

Cemimax DL10

BULK FILLING COMPOUND

Levelling cement flooring compound to economically bulk fill and raise floors

DESCRIPTION

DL10 is an advanced cement and polymer based levelling compound with special aggregates. DL10 is formulated with high flow performance for levelling work on installation of thick layers. DL10 is very suitable for quick setting preparation solutions and also can be used as a fast set screed with low ratio water mixing.

PRODUCT PROPERTIES/BENEFITS

Plastic dry cement mortar with finely graded fillers. When mixed with water, produces a hydraulic-setting smoothing compound with good flow properties and high coverage.

COMPOSITION

Special cements, mineral fillers, polyvinyl-acetate-co-polymers, flow agents and additives.

- Easy application
- Quick setting
- Superior flow – fast application
- Can be used as fast set screed
- High-depth limitation (1.5mm to 150mm)
- Compatible with other cemimax leveling compounds

TECHNICAL DATA

Compressive Strength

After 1 Day Approx. 15mpa

After 7 Days Approx. 20mpa

After 28 Days Approx. 30mpa

Tensile Bending Strength

After 1 Day Approx. 5mpa

After 7 Days Approx. 7mpa

After 28 Days Approx. 8mpa

Pack-size: 20kg bag

Shelf-life: 6-12 months

Coverage: Approximately 1.5kg Powder/mm/m²

Dry time: 10-30mins

Working time: 15-25mins

THICKNESS

DL10 can be applied from 10 mm to 150 mm thickness in one application.

SUBFLOOR PREPARATION

- The substrate must be sound, free from cracks, dry, clean and free from materials which would impair adhesion.
- Test the substrate according to applicable standards and report any deficiencies.
- Brush, abrade, grind or shot-blast any weak surface sections or areas which will not accept adhesion.
- Thoroughly vacuum to remove loose material and dust.

- According to type and condition of the subfloor, apply suitable Cemimax primer.
- Allow primers to dry thoroughly.

APPLICATION

1. Mixing Ratio

Use 2.7 liters of water to 20 kg of powder when used as a leveller.

Use 2.3 liters of water to 20 kg of powder when used as a fast set screed.

2. Pour the mixture on the area to be applied, spread the material uniformly to required thickness using toothed rake. It is the next step to remove entranced air by particle roller.

3. Drying time at 20°C is approx 4 hours for walked on. Poor air-flow and lower temperatures will significantly affect drying times.

IMPORTANT NOTES

- Minimum shelf-life 12 months in original packaging and in dry storage conditions. Tightly seal opened packaging and use the contents as quickly as possible.
- Best applied at 18-25°C, floor temperature above 15°C and relative humidity below 75%. Low temperatures and high humidity delay setting, drying and readiness for covering. High temperatures shorten the working time. Therefore use the coldest possible mixing water during the summer.
- Protect freshly smoothed surfaces from draughts direct sunlight and influences of heat.
- The product should be protected against frost and direct light during transportation, storage and application.
- Application temperature should not be lower than 5°C.

DISPOSAL

Dispose of empty packaging according to local regulations.

